

LEGA RAME - STAGNO [BRONZO]

ASTM B584 C83600

Composition in % [mass fraction]			Tensile strength	0,2 % proof strength	Elongation	Brinell hardness
Element	min.	MAX.	<i>R_m</i> MPa min.	<i>R_{p0,2}</i> MPa min.	<i>A</i> % min.	HBW min.
Cu	84,0	86,0	207	97	20	
Sn	4,0	6,0				
Pb	4,0	6,0				
Zn	4,0	6,0				
Ni	–	1,0				