

LEGA RAME - STAGNO [BRONZO]

ASTM B584 C83600

Composition in % [mass fraction]			Tensile strength	0,2 % proof strength	Elongation	Brinell hardness
Element	min.	MAX.	<i>R_m</i> MPa min.	<i>R_{p0,2}</i> MPa min.	<i>A</i> % min.	HBW min.
Cu	84,0	86,0	207	97	20	
Sn	4,0	6,0				
Pb	4,0	6,0				
Zn	4,0	6,0				
Ni	–	1,0				

Fonderia Caglioni srl

Sede Legale
Sedi Operative

Via Aldo Moro, 3 — 24050 Orio al Serio (BG)
Via Aldo Moro, 3-14 — 24050 Orio al Serio (BG)
T +39 035 4522140 — E-mail info@fonderiacaglioni.it
C.F./P.IVA 01486010166 — Reg. Imp. BG 23092 - R.E.A. 211939 — Cap. Soc. € 49.400 i.v.

www.fonderiacaglioni.it