

LEGA RAME - STAGNO [BRONZO]

ASTM B584 C90500

Composition in % [mass fraction]			Tensile strength	0,2 % proof strength	Elongation	Brinell hardness
Element	min.	MAX.	<i>R_m</i> MPa min.	<i>R_{p0,2}</i> MPa min.	<i>A</i> % min.	HBW min.
Cu	86,0	89,0	276	124	20	
Sn	9,0	11,0				
Pb	–	0,30				
Zn	1,0	3,0				
Ni	–	1,0				