

LEGA RAME - STAGNO [BRONZO]

ASTM B584 C92200

Composition in % [mass fraction]			Tensile strength	0,2 % proof strength	Elongation	Brinell hardness
Element	min.	MAX.	Rm MPa min.	Rp0,2 MPa min.	A % min.	HBW min.
Cu	86,0	90,0	234	110	22	
Sn	5,5	6,5				
Pb	1,0	2,0				
Zn	3,0	5,0				
Ni	–	1,0				